Rev.-Nr. 3: 2017-01-17





LOXIOL<sup>®</sup> 2307

Lubricant (external)

## **Description**

LOXIOL® 2307 is a lubricant combination based on complex ester.

## **General Appearance**

- ✓ White to slightly yellow, solid
- ✓ Odorless
- ✓ Available as fine grained powder

# **Specified Data**

Parameter	Value	Test Method	
Melting point (°C)	80 - 90	Q-P 1583	
Acid value (mg KOH/g)	0 - 15	DIN EN ISO 2114	
Hydroxyl value (mg KOH/g)	0 - 15	DIN 53240	

## **Properties and Applications**

LOXIOL® 2307 is a strong external lubricant and release agent for rigid PVC and C-PVC. Its high dropping point, 80 - 90 °C and low volatility makes it thermal stable in a wide temperature range. Its influence on the vicat softening temperature is low.

LOXIOL® 2307 is suited for extrusion of rigid PVC and C-PVC pipe and profile, and also for injection molding.



Rev.-Nr. 3: 2017-01-17





Recommended Dosage

0.1 - 1.2 phr

## **Certifications**

LOXIOL® 2307 is registered in compliance with the EU REACH regulation.

## Health and Safety Information

Please review our Safety Data Sheet for best practices when using this material.

#### Packaging Sizes

Bags, 25 kg Big bags, 900 kg

#### **Storage and Handling**

The recommended storage for LOXIOL<sup>®</sup> 2307 is at room temperature. If stored in original sealed packaging, LOXIOL<sup>®</sup> 2307 should be stable for at least 24 months from the date of manufacture.

Emery Oleochemicals GmbH T | +49 211 5611 2000 E | gp.europe@emeryoleo.com Emery Oleochemicals LLC T | +1 513 762 2500 E | gp.americas@emeryoleo.com Emery Oleochemicals (M) Sdn Bhd T | +603 3326 8686 E | gp.asia@emeryoleo.com

**Disclaimer:** The content in this document is provided on an "as is" and "as available" basis purely for informational purposes and, unless and to the extent specifically agreed otherwise for a sales transaction, does not constitute any warranty, whether express, implied or statutory, including but not limited to warranties or guarantees of merchantability, fitness or suitability for a particular purpose nor any representations of a binding nature. EMERY OLEOCHEMICALS EXPRESSLY DISCLAIMS ANY RESPONSI-BILITY FOR THE SUITABILITY OF THE PRODUCTS FOR ANY SPECIFIC OR PARTICULAR PURPOSES INTENDED BY THE USER. Suggestions for the use and application of the products and guide formulations are for informational purposes only and you are advised to carry out any necessary steps to test the suitability of the products for your intended processes and purposes. You are solely responsible for compliance with all applicable laws and regulations in use of the products including any third party intellectual property rights and shall bear all liability or isk arising from use of the products. All indications marked with a TM or ® symbol are trademarks belonging to legal entities within the Emery Oleochemicals group of companies.